

I. Stern & Co. Inc

Random Copolymer Polypropylene Product Data Sheet

2335C – Prime Clarified Random Copolymer Polypropylene

Features

- High flow characteristics
- FDA
- See-through and contact clarity
- Food contact acceptable

Applications

- containers
- bottles
- storage boxes
- toys

<u>Property</u>	<u>Units</u>	<u>ASTM</u>	<u>Typical Value</u>
Melt Flow Rate	g/10 min	D1238	35
Notched Izod 73 deg. F (IM)	ft-lb/in	D256	1.3
Density @ 23 deg. C	g/cm ³	D792	0.902
Tensile Yield	psi	D638	4100
Yield Elongation	%	D638	13
Flexural Modulus (procedure A) 1% Secant	psi	D790	145,000
DTUL @ 66psi Unannealed	deg F	D648	180
Haze	%	D1003	10

I. Stern has no control over the use to which others may put this material, it does not guarantee that the same results, as those described will be obtained. I. Stern & Co. does not guarantee the effectiveness or safety of any material for the design as well as the suitability of the material or designs of both for his own particular use. Statements concerning possible or suggested uses of the materials or designs described herein are not to be construed as recommendations for use of such materials or designs.